

Southwest Fireproofing Type 5 GP, 5 MD, 7 GP and 7 HD

N791 - Restrained and Unrestrained Beam Ratings

D949 - Unrestrained Beam Ratings only

Minimum Thickness Required on Beam for Size Indictaed, in.

Normal Weight Concrete

Unrestrained Beam Rating					Member W/D	Restrained Beam Rating*				
1 Hr	1.5 Hr	2 Hr	3 Hr	4 Hr		1 Hr	1.5 Hr	2 Hr	3 Hr	4 Hr
0.42	0.63	0.91	1.26	1.82	W4x13 0.65	0.42	0.42	0.63	1.05	1.40
0.42	0.63	0.91	1.26	1.82	W5x16 0.65	0.42	0.42	0.63	1.05	1.40
0.39	0.58	0.84	1.16	1.67	W5x19 0.76	0.39	0.39	0.58	0.97	1.29
0.53	0.80	1.15	1.59	2.30	W6x9 0.39	0.53	0.53	0.80	1.33	1.77
0.47	0.71	1.02	1.42	2.05	W6x12 0.51	0.47	0.47	0.71	1.18	1.58
0.42	0.63	0.90	1.25	1.81	W6x16 0.66	0.42	0.42	0.63	1.04	1.39
0.41	0.62	0.90	1.24	1.79	W6x20 0.67	0.41	0.41	0.62	1.03	1.38
0.38	0.55	0.80	1.11	1.60	W6x26 0.82	0.38	0.38	0.55	0.92	1.23
0.54	0.81	1.17	1.62	2.35	W8x10 0.37	0.54	0.54	0.81	1.35	1.80
0.49	0.74	1.06	1.47	2.13	W8x13 0.47	0.49	0.49	0.74	1.23	1.64
0.46	0.69	1.00	1.38	2.00	W8x15 0.54	0.46	0.46	0.69	1.15	1.54
0.45	0.67	0.97	1.35	1.95	W8x18 0.57	0.45	0.45	0.67	1.12	1.50
0.42	0.63	0.90	1.25	1.81	W8x21 0.66	0.42	0.42	0.63	1.04	1.39
0.41	0.61	0.88	1.22	1.76	W8x24 0.69	0.41	0.41	0.61	1.02	1.36
0.38	0.56	0.81	1.13	1.63	W8x28 0.80	0.38	0.38	0.56	0.94	1.25
0.38	0.57	0.82	1.13	1.64	W8x31 0.79	0.38	0.38	0.57	0.94	1.26
0.38	0.53	0.77	1.06	1.54	W8x35 0.88	0.38	0.38	0.53	0.89	1.18
0.38	0.49	0.71	0.98	1.42	W8x40 1.00	0.38	0.38	0.49	0.82	1.09
0.38	0.44	0.64	0.88	1.28	W8x48 1.18	0.38	0.38	0.44	0.74	0.98
0.38	0.39	0.57	0.78	1.13	W8x58 1.41	0.38	0.38	0.39	0.65	0.87
0.38	0.38	0.51	0.71	1.03	W8x67 1.61	0.38	0.38	0.38	0.59	0.79
0.54	0.80	1.16	1.61	2.32	W10x12 0.38	0.54	0.54	0.80	1.34	1.79
0.49	0.73	1.05	1.46	2.11	W10x15 0.48	0.49	0.49	0.73	1.22	1.62
0.46	0.69	1.00	1.38	2.00	W10x17 0.54	0.46	0.46	0.69	1.15	1.54
0.44	0.66	0.96	1.32	1.91	W10x19 0.59	0.44	0.44	0.66	1.10	1.47
0.44	0.66	0.96	1.32	1.91	W10x22 0.59	0.44	0.44	0.66	1.10	1.47
0.41	0.61	0.88	1.22	1.76	W10x26 0.69	0.41	0.41	0.61	1.02	1.36
0.38	0.57	0.82	1.13	1.64	W10x30 0.79	0.38	0.38	0.57	0.94	1.26
0.38	0.57	0.83	1.15	1.66	W10x33 0.77	0.38	0.38	0.57	0.96	1.28
0.38	0.53	0.76	1.05	1.52	W10x39 0.90	0.38	0.38	0.53	0.88	1.17
0.38	0.48	0.70	0.97	1.40	W10x46 1.03	0.38	0.38	0.48	0.81	1.07
0.38	0.50	0.72	0.99	1.43	W10x49 0.99	0.38	0.38	0.50	0.83	1.10
0.38	0.47	0.67	0.93	1.35	W10x54 1.09	0.38	0.38	0.47	0.78	1.04
0.38	0.44	0.63	0.88	1.26	W10x60 1.20	0.38	0.38	0.44	0.73	0.97
0.38	0.40	0.58	0.80	1.16	W10x68 1.36	0.38	0.38	0.40	0.67	0.89
0.38	0.38	0.54	0.74	1.07	W10x77 1.52	0.38	0.38	0.38	0.62	0.83
0.38	0.38	0.49	0.68	0.98	W10x88 1.72	0.38	0.38	0.38	0.57	0.75
0.38	0.38	0.45	0.62	0.90	W10x100 1.93	0.38	0.38	0.38	0.52	0.69
0.38	0.38	0.42	0.57	0.83	W10x112 2.14	0.38	0.38	0.38	0.48	0.64
0.53	0.79	1.14	1.58	2.28	W12x14 0.40	0.53	0.53	0.79	1.31	1.75
0.50	0.75	1.08	1.50	2.17	W12x16 0.45	0.50	0.50	0.75	1.25	1.67
0.46	0.70	1.01	1.39	2.01	W12x19 0.53	0.46	0.46	0.70	1.16	1.55
0.43	0.65	0.94	1.30	1.88	W12x22 0.61	0.43	0.43	0.65	1.08	1.45
0.44	0.66	0.95	1.31	1.90	W12x26 0.60	0.44	0.44	0.66	1.09	1.46
0.41	0.61	0.88	1.22	1.76	W12x30 0.69	0.41	0.41	0.61	1.02	1.36

Southwest Fireproofing Type 5 GP, 5 MD, 7 GP and 7 HD

N791 - Restrained and Unrestrained Beam Ratings

D949 - Unrestrained Beam Ratings only

Minimum Thickness Required on Beam for Size Indictaed, in.

Normal Weight Concrete

Unrestrained Beam Rating					Member W/D		Restrained Beam Rating*				
1 Hr	1.5 Hr	2 Hr	3 Hr	4 Hr			1 Hr	1.5 Hr	2 Hr	3 Hr	4 Hr
0.38	0.57	0.82	1.13	1.64	W12x35	0.79	0.38	0.38	0.57	0.94	1.26
0.38	0.54	0.78	1.09	1.57	W12x40	0.85	0.38	0.38	0.54	0.91	1.21
0.38	0.51	0.73	1.02	1.47	W12x45	0.95	0.38	0.38	0.51	0.85	1.13
0.38	0.48	0.69	0.96	1.39	W12x50	1.04	0.38	0.38	0.48	0.80	1.07
0.38	0.50	0.72	0.99	1.43	W12x53	0.99	0.38	0.38	0.50	0.83	1.10
0.38	0.48	0.69	0.96	1.39	W12x54	1.04	0.38	0.38	0.48	0.80	1.07
0.38	0.47	0.68	0.94	1.35	W12x58	1.08	0.38	0.38	0.47	0.78	1.04
0.38	0.47	0.67	0.93	1.35	W12x65	1.09	0.38	0.38	0.47	0.78	1.04
0.38	0.44	0.63	0.88	1.26	W12x72	1.20	0.38	0.38	0.44	0.73	0.97
0.38	0.41	0.59	0.82	1.19	W12x79	1.32	0.38	0.38	0.41	0.68	0.91
0.38	0.39	0.56	0.77	1.12	W12x87	1.44	0.38	0.38	0.39	0.64	0.86
0.38	0.38	0.52	0.73	1.05	W12x96	1.57	0.38	0.38	0.38	0.60	0.81
0.38	0.38	0.49	0.68	0.98	W12x106	1.73	0.38	0.38	0.38	0.56	0.75
0.38	0.38	0.45	0.62	0.90	W12x120	1.94	0.38	0.38	0.38	0.52	0.69
0.38	0.38	0.41	0.57	0.82	W12x136	2.17	0.38	0.38	0.38	0.47	0.63
0.38	0.38	0.38	0.53	0.76	W12x152	2.40	0.38	0.38	0.38	0.44	0.58
0.38	0.38	0.38	0.48	0.70	W12x170	2.66	0.38	0.38	0.38	0.40	0.54
0.38	0.38	0.38	0.45	0.64	W12x190	2.93	0.38	0.38	0.38	0.38	0.50
0.38	0.38	0.38	0.41	0.60	W12x210	3.21	0.38	0.38	0.38	0.38	0.46
0.38	0.38	0.38	0.39	0.56	W12x230	3.47	0.38	0.38	0.38	0.38	0.43
0.38	0.38	0.38	0.38	0.52	W12x262	3.76	0.38	0.38	0.38	0.38	0.40
0.38	0.38	0.38	0.38	0.48	W12x279	4.10	0.38	0.38	0.38	0.38	0.38
0.38	0.38	0.38	0.38	0.45	W12x305	4.41	0.38	0.38	0.38	0.38	0.38
0.38	0.38	0.38	0.38	0.42	W12x336	4.78	0.38	0.38	0.38	0.38	0.38
0.47	0.70	1.02	1.41	2.03	W14x22	0.52	0.47	0.47	0.70	1.17	1.56
0.43	0.65	0.94	1.30	1.88	W14x26	0.61	0.43	0.43	0.65	1.08	1.45
0.43	0.64	0.92	1.28	1.85	W14x30	0.63	0.43	0.43	0.64	1.07	1.42
0.40	0.60	0.87	1.20	1.74	W14x34	0.71	0.40	0.40	0.60	1.00	1.34
0.38	0.57	0.82	1.13	1.64	W14x38	0.79	0.38	0.38	0.57	0.94	1.26
0.38	0.54	0.78	1.09	1.57	W14x43	0.85	0.38	0.38	0.54	0.91	1.21
0.38	0.51	0.74	1.02	1.48	W14x48	0.94	0.38	0.38	0.51	0.85	1.14
0.38	0.48	0.70	0.97	1.40	W14x53	1.03	0.38	0.38	0.48	0.81	1.07
0.38	0.47	0.68	0.94	1.36	W14x61	1.07	0.38	0.38	0.47	0.79	1.05
0.38	0.44	0.64	0.88	1.27	W14x68	1.19	0.38	0.38	0.44	0.73	0.98
0.38	0.42	0.61	0.84	1.21	W14x74	1.28	0.38	0.38	0.42	0.70	0.93
0.38	0.39	0.57	0.78	1.13	W14x82	1.41	0.38	0.38	0.39	0.65	0.87
0.38	0.42	0.61	0.84	1.22	W14x90	1.27	0.38	0.38	0.42	0.70	0.94
0.38	0.40	0.57	0.79	1.14	W14x99	1.39	0.38	0.38	0.40	0.66	0.88
0.38	0.38	0.53	0.74	1.07	W14x109	1.53	0.38	0.38	0.38	0.62	0.82
0.38	0.38	0.50	0.69	1.00	W14x120	1.67	0.38	0.38	0.38	0.58	0.77
0.38	0.38	0.47	0.65	0.94	W14x132	1.83	0.38	0.38	0.38	0.54	0.72
0.38	0.38	0.45	0.62	0.90	W14x145	1.94	0.38	0.38	0.38	0.52	0.69
0.38	0.38	0.42	0.58	0.84	W14x159	2.11	0.38	0.38	0.38	0.48	0.65
0.38	0.38	0.40	0.55	0.80	W14x176	2.25	0.38	0.38	0.38	0.46	0.61
0.38	0.38	0.39	0.54	0.78	W14x193	2.32	0.38	0.38	0.38	0.45	0.60

Southwest Fireproofing Type 5 GP, 5 MD, 7 GP and 7 HD

N791 - Restrained and Unrestrained Beam Ratings

D949 - Unrestrained Beam Ratings only

Minimum Thickness Required on Beam for Size Indictaed, in.

Normal Weight Concrete

Unrestrained Beam Rating					Member W/D		Restrained Beam Rating*				
1 Hr	1.5 Hr	2 Hr	3 Hr	4 Hr			1 Hr	1.5 Hr	2 Hr	3 Hr	4 Hr
0.38	0.38	0.38	0.47	0.68	W14x211	2.74	0.38	0.38	0.38	0.39	0.52
0.38	0.38	0.38	0.44	0.63	W14x233	3.00	0.38	0.38	0.38	0.38	0.49
0.38	0.38	0.38	0.41	0.59	W14x257	3.27	0.38	0.38	0.38	0.38	0.45
0.38	0.38	0.38	0.38	0.55	W14x283	3.57	0.38	0.38	0.38	0.38	0.42
0.38	0.38	0.38	0.38	0.51	W14x311	3.88	0.38	0.38	0.38	0.38	0.39
0.38	0.38	0.38	0.38	0.47	W14x342	4.21	0.38	0.38	0.38	0.38	0.38
0.38	0.38	0.38	0.38	0.45	W14x370	4.51	0.38	0.38	0.38	0.38	0.38
0.38	0.38	0.38	0.38	0.42	W14x398	4.80	0.38	0.38	0.38	0.38	0.38
0.38	0.38	0.38	0.38	0.40	W14x426	5.09	0.38	0.38	0.38	0.38	0.38
0.38	0.38	0.38	0.38	0.38	W14x455	5.38	0.38	0.38	0.38	0.38	0.38
0.38	0.38	0.38	0.38	0.38	W14x500	5.82	0.38	0.38	0.38	0.38	0.38
0.38	0.38	0.38	0.38	0.38	W14x550	6.30	0.38	0.38	0.38	0.38	0.38
0.38	0.38	0.38	0.38	0.38	W14x605	6.80	0.38	0.38	0.38	0.38	0.38
0.46	0.68	0.99	1.37	1.98	W16x26	0.55	0.46	0.46	0.68	1.14	1.52
0.42	0.63	0.91	1.26	1.82	W16x31	0.65	0.42	0.42	0.63	1.05	1.40
0.41	0.61	0.88	1.22	1.76	W16x36	0.69	0.41	0.41	0.61	1.02	1.36
0.39	0.58	0.84	1.16	1.67	W16x40	0.76	0.39	0.39	0.58	0.97	1.29
0.38	0.54	0.78	1.09	1.57	W16x45	0.85	0.38	0.38	0.54	0.91	1.21
0.38	0.51	0.74	1.02	1.48	W16x50	0.94	0.38	0.38	0.51	0.85	1.14
0.38	0.47	0.68	0.94	1.36	W16x67	1.07	0.38	0.38	0.47	0.79	1.05
0.38	0.47	0.68	0.94	1.36	W16x77	1.07	0.38	0.38	0.47	0.79	1.05
0.38	0.43	0.63	0.87	1.25	W16x89	1.22	0.38	0.38	0.43	0.72	0.96
0.38	0.38	0.53	0.73	1.05	W16x100	1.56	0.38	0.38	0.38	0.61	0.81
0.42	0.63	0.90	1.25	1.81	W18x35	0.66	0.42	0.42	0.63	1.04	1.39
0.39	0.58	0.84	1.16	1.67	W18x40	0.76	0.39	0.39	0.58	0.97	1.29
0.38	0.54	0.78	1.08	1.56	W18x46	0.86	0.38	0.38	0.54	0.90	1.20
0.38	0.54	0.77	1.07	1.55	W18x50	0.87	0.38	0.38	0.54	0.89	1.19
0.38	0.51	0.73	1.02	1.47	W18x55	0.95	0.38	0.38	0.51	0.85	1.13
0.38	0.48	0.70	0.97	1.40	W18x60	1.03	0.38	0.38	0.48	0.81	1.07
0.38	0.46	0.67	0.92	1.33	W18x65	1.11	0.38	0.38	0.46	0.77	1.02
0.38	0.44	0.63	0.87	1.26	W18x71	1.21	0.38	0.38	0.44	0.73	0.97
0.38	0.46	0.67	0.92	1.33	W18x76	1.11	0.38	0.38	0.46	0.77	1.02
0.38	0.43	0.62	0.86	1.24	W18x88	1.24	0.38	0.38	0.43	0.71	0.95
0.38	0.40	0.57	0.79	1.14	W18x97	1.39	0.38	0.38	0.40	0.66	0.88
0.38	0.38	0.54	0.74	1.07	W18x106	1.52	0.38	0.38	0.38	0.62	0.83
0.38	0.38	0.50	0.69	1.00	W18x119	1.68	0.38	0.38	0.38	0.58	0.77
0.39	0.59	0.86	1.18	1.71	W21x44	0.73	0.39	0.39	0.59	0.99	1.32
0.38	0.55	0.80	1.10	1.59	W21x50	0.83	0.38	0.38	0.55	0.92	1.22
0.38	0.51	0.74	1.03	1.49	W21x57	0.93	0.38	0.38	0.51	0.86	1.14
0.38	0.51	0.74	1.02	1.48	W21x62	0.94	0.38	0.38	0.51	0.85	1.14
0.38	0.48	0.70	0.97	1.40	W21x68	1.03	0.38	0.38	0.48	0.81	1.07
0.38	0.43	0.62	0.86	1.24	W21x83	1.24	0.38	0.38	0.43	0.71	0.95
0.38	0.40	0.57	0.80	1.15	W21x93	1.38	0.38	0.38	0.40	0.66	0.88
0.38	0.42	0.60	0.83	1.20	W21x101	1.29	0.38	0.38	0.42	0.69	0.93
0.38	0.39	0.57	0.78	1.13	W21x111	1.41	0.38	0.38	0.39	0.65	0.87

Southwest Fireproofing Type 5 GP, 5 MD, 7 GP and 7 HD
N791 - Restrained and Unrestrained Beam Ratings
D949 - Unrestrained Beam Ratings only

Minimum Thickness Required on Beam for Size Indictaed, in.
Normal Weight Concrete

Unrestrained Beam Rating					Member W/D		Restrained Beam Rating*				
1 Hr	1.5 Hr	2 Hr	3 Hr	4 Hr			1 Hr	1.5 Hr	2 Hr	3 Hr	4 Hr
0.38	0.38	0.53	0.74	1.06	W21x122	1.54	0.38	0.38	0.38	0.61	0.82
0.38	0.38	0.45	0.70	1.01	W21x132	1.66	0.38	0.38	0.38	0.52	0.77
0.38	0.38	0.42	0.65	0.94	W21x147	1.83	0.38	0.38	0.38	0.49	0.72
0.38	0.50	0.72	1.11	1.60	W24x55	0.82	0.38	0.38	0.50	0.83	1.23
0.38	0.47	0.67	1.04	1.50	W24x62	0.92	0.38	0.38	0.47	0.78	1.15
0.38	0.46	0.67	1.03	1.49	W24x68	0.93	0.38	0.38	0.46	0.77	1.14
0.38	0.44	0.63	0.97	1.40	W24x76	1.02	0.38	0.38	0.44	0.73	1.08
0.38	0.41	0.59	0.91	1.32	W24x84	1.13	0.38	0.38	0.41	0.68	1.01
0.38	0.38	0.55	0.85	1.22	W24x94	1.26	0.38	0.38	0.38	0.64	0.94
0.38	0.39	0.56	0.87	1.25	W24x104	1.22	0.38	0.38	0.39	0.65	0.96
0.38	0.38	0.52	0.80	1.16	W24x117	1.36	0.38	0.38	0.38	0.60	0.89
0.38	0.38	0.48	0.74	1.07	W24x131	1.52	0.38	0.38	0.38	0.56	0.83
0.38	0.38	0.45	0.69	1.00	W24x146	1.68	0.38	0.38	0.38	0.52	0.77
0.38	0.38	0.42	0.64	0.93	W24x162	1.85	0.38	0.38	0.38	0.48	0.71
0.38	0.44	0.63	0.97	1.40	W27x84	1.02	0.38	0.38	0.44	0.73	1.08
0.38	0.41	0.59	0.91	1.32	W27x94	1.13	0.38	0.38	0.41	0.68	1.01
0.38	0.39	0.56	0.86	1.24	W27x102	1.23	0.38	0.38	0.39	0.65	0.96
0.38	0.38	0.52	0.80	1.16	W27x114	1.36	0.38	0.38	0.38	0.60	0.89
0.38	0.38	0.48	0.74	1.07	W27x146	1.53	0.38	0.38	0.38	0.55	0.82
0.38	0.38	0.45	0.69	1.00	W27x161	1.68	0.38	0.38	0.38	0.52	0.77
0.38	0.38	0.42	0.64	0.93	W27x178	1.85	0.38	0.38	0.38	0.48	0.71
0.38	0.42	0.60	0.93	1.34	W30x99	1.10	0.38	0.38	0.42	0.69	1.03
0.38	0.39	0.57	0.88	1.26	W30x108	1.20	0.38	0.38	0.39	0.66	0.97
0.38	0.38	0.54	0.84	1.21	W30x116	1.28	0.38	0.38	0.38	0.63	0.93
0.38	0.38	0.52	0.80	1.16	W30x124	1.37	0.38	0.38	0.38	0.60	0.89
0.38	0.38	0.50	0.76	1.10	W30x132	1.46	0.38	0.38	0.38	0.57	0.85
0.38	0.38	0.45	0.70	1.01	W30x173	1.66	0.38	0.38	0.38	0.52	0.77
0.38	0.38	0.42	0.65	0.94	W30x191	1.82	0.38	0.38	0.38	0.49	0.72
0.38	0.38	0.39	0.61	0.88	W30x211	2.00	0.38	0.38	0.38	0.45	0.67
0.38	0.40	0.57	0.88	1.27	W33x118	1.19	0.38	0.38	0.40	0.66	0.98
0.38	0.38	0.54	0.82	1.19	W33x130	1.31	0.38	0.38	0.38	0.62	0.92
0.38	0.38	0.51	0.78	1.13	W33x141	1.41	0.38	0.38	0.38	0.59	0.87
0.38	0.38	0.49	0.75	1.08	W33x152	1.51	0.38	0.38	0.38	0.56	0.83
0.38	0.38	0.43	0.66	0.96	W33x201	1.78	0.38	0.38	0.38	0.50	0.74

These beam protection thicknesses have been calculated for the convenience of users, in accordance with "6. Adjustment of Thickness of Spray-applied Fire Resistive Materials for Restrained and Unrestrained Beams", as detailed in the UL FireResistance Directory - Volume 1, 2010, page 10. While we have taken care to be as accurate as possible, we will not be held responsible for errors or omissions. If any discrepancy is found between these tables and the UL Design information, the UL Design information shall govern.

* When used to adjust the material thickness for a **Restrained** beam the use of this procedure is limited to steel sections classified as **compact** in accordance with the *Specification for the Design of Structural Steel Buildings* by the American Institute of Steel Construction. Refer to the UL Fire Resistance Directory.